

TEMPERED GLASS					
Color	Thickness		Daylight Transmittance	Weight	
	Inch	mm		lb/ft <sup>2</sup>	kg/m <sup>2</sup>
Clear	3/32"	2.5	91%	1.2	6.02
	1/8"	3	90%	1.7	8.03
	5/32"	4	90%	2	10.04
	3/16"	5	90%	2.5	12.05
	1/4"	6	89%	3.3	16.07
	5/16"	8	88%	4.1	20.08
	3/8"	10	88%	4.9	24.10
	1/2"	12	87%	6.6	32.13
	5/8"	16	85%	8.2	40.16
	3/4"	19	84%	9.9	48.20
	1"	25	82%	13.2	64.26
Gray	1/8"	3	62%	1.7	8.03
	3/16"	5	50%	2.5	12.05
	1/4"	6	45%	3.3	16.07
	5/16"	8	34%	4.1	20.08
	3/8"	10	28%	4.9	24.10
	1/2"	12	19%	6.6	32.13
Graylite 14	1/4"	6	14%	3.3	16.07
Bronze	1/8"	3	68%	1.7	8.03
	3/16"	5	58%	2.5	12.05
	1/4"	6	54%	3.3	16.07
	5/16"	8	43%	4.1	20.08
	3/8"	10	38%	4.9	24.10
	1/2"	12	28%	6.6	32.13
Blue-Green	1/4"	6	76%	3.3	16.07
	5/16"	8	71%	4.1	20.08
	3/8"	10	67%	4.9	24.10
EverGreen	1/8"	3	77%	1.7	8.03
	3/16"	5	70%	2.5	12.05
	1/4"	6	66%	3.3	16.07

LAMINATED GLASS					
Color	Thickness		Daylight Transmittance	Weight	
	Inch	mm		lb/ft <sup>2</sup>	kg/m <sup>2</sup>
Clear	7/32"	6	89%	2.85	14.29
	3/8"	10	89%	4.9	24.10
	1/2"	12	89%	6.6	32.13
	3/4"	19	77%	9.9	48.20
Light Gray	7/32"	6	44%	2.85	14.29
	3/8"	10	44%	4.9	24.10
	1/2"	12	44%	6.6	32.13
Dark Gray	7/32"	6	28%	2.85	14.29
	3/8"	10	28%	4.9	24.10
Bronze	7/32"	6	52%	2.85	14.29
	3/8"	10	52%	4.9	24.10
	1/2"	12	52%	6.6	32.13
Light Green	7/32"	6	73%	2.85	14.29

POLYCARBONATE					
Color	Thickness		Daylight Transmittance	Weight	
	Inch	mm		lb/ft <sup>2</sup>	kg/m <sup>2</sup>
Clear	1/8"	3	86%	0.78	3.80
	1/4"	6	82%	1.56	5.94
	3/8"	10	79%	2.34	13.90
	1/2"	12	75%	3.12	15.23
Gray	1/8"	3	50%	0.78	3.80
	1/4"	6	50%	1.56	5.94
	3/8"	10	50%	2.34	13.90
	1/2"	12	50%	3.12	15.23
Bronze	1/8"	3	50%	0.78	3.80
	1/4"	6	50%	1.56	5.94
	3/8"	10	50%	2.34	13.90
	1/2"	12	50%	3.12	15.23